



Datenblatt Filz NFX 3.0

FEATURE	TEST METHOD	SPECIFIED VALUE	UNIT	REMARKS
FIBER COMPOSITION		100% PES		
STRUCTURE OF THE SURFACE	Visual	According to the released sample		
WEIGHT	ISO 9073-1	500 ± 10%	g/m ²	
THICKNESS	ISO 9073-2	3,00 ± 10%	mm	
COLOUR FASTNESS				
TO COMMERCIAL & DOMESTIC LAUNDERING	ISO 105-C06	4 - 5	GS	Grey Scale
TO RUBBING	ISO 105-X12	4 - 5	GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
TO IRONING	ISO 105-X11	5	GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
Wet		4 - 5		
TO ORGANIC SOLVENTS	ISO 105-X05	4 - 5	GS	Grey Scale
TO ARTIFICIAL LIGHT	ISO 105-B02	6	BS	Blue Scale
DIMENSIONAL STABILITY	(60°C)	Max. 1%	%	
WIDTH	Tape measure	1	m	
ROLL LENGTH	Countmeter	20	m	

Huttwil 1.8.2025